

**SYDNEY**

25 – 27 Green St  
East Botany, NSW 2019  
Ph: +61 2 9666 3788  
Fax: +61 2 9666 4805

**MELBOURNE**

29 Trade Place  
Vermont, VIC 3133  
Ph: 03 9872 4033  
Fax: 03 9872 4099

**BRISBANE**

Unit 6/5 Deakin Street  
Brendale, QLD 4500  
Ph: 07 3205 8510  
Fax: 07 3205 9616

**SINGAPORE**

H.K. Moey  
9 Elias Terrace  
Singapore 519772  
Ph: +65 6582 8103  
Fax: +65 6584 8100  
Mobile: +65 9751 0026



# TECHNICAL DATA

## Erelease LP 57

WAX BASED MOULD RELEASE FOR FLEXIBLE AND RIGID  
POLYURETHANE FOAM

**Erelease LP 57** is a low viscosity liquid mould release agent based on a blend of waxes with excellent releasing in hard-to-reach zones.

### APPLICATION

**Erelease LP 57** is applied by air-less spray with spray gun with reduced air pressure.

**Erelease LP 57** is primarily developed for spray application, it may also be brush or wiped applied, leaving a thin film of waxes thus allowing reproduction of the finest detail.

### PRODUCT SPECIFICATION

<b>Colour</b>	White liquid, solvent odour
<b>Specific gravity</b>	0.7 @ 20°C
<b>Flammability Limits</b>	1 – 7 % (V)
<b>Flashpoint (°C)</b>	-5°C

### APPLICATION DETAILS

Thoroughly clean the mould with a suitable solvent to remove any previous release or contamination. Wipe dry with a clean cloth.

Using conventional spray equipment (10 – 50 cm from surface), apply **Erelease LP 57** to the clean moulds. Alternatively, wipe or brush application may be used.

To pre-treat or condition the clean mould, apply three even coats (allow solvent to flash off between coats). For optimum surface results, lightly buff the inside of the mould with a clean, lint-free cotton cloth after drying.

Reapply after each demould to ensure the mould is clean and adequate release.

**CAUTION:** Use in well ventilated areas. Avoid breathing vapours or fumes. Avoid contact with skin and eyes. If contact occurs, wash immediately with soap and water. Keep away from heat, sparks and flames and stirring before and during use. Do not store outdoors in case of freezing.

This information is of general nature and is supplied without recommendation of guarantee. It does not make claim to be free from patent infringement. Properties shown are typical and do not imply specification tolerances. Era Polymers cannot accept liability for loss or damage through use. Whilst these technical details are based on expert knowledge, practical experience and laboratory testing, successful application depends upon the nature and conditions in which the products are supplied. Users must, by comprehensive testing, evaluate this product in their own application.

