



**Era Polymers Pty. Ltd.**  
25-27 Green Street, Banksmeadow  
Sydney, NSW 2019  
AUSTRALIA  
www.erapol.com.au

## Erapol EMP95A

POLYETHER (PPG/PTMEG) TDI PREPOLYMER

### TECHNICAL DATASHEET

**Erapol EMP95A** is a liquid prepolymer based on polyols that provide physical properties between Erapol High Performance Elastomers and Erapol Low Cost Elastomers.

Polymers made from **Erapol EMP95A** exhibit outstanding abrasion resistance, high load bearing capability, low heat build up and excellent low temperature flexibility.

#### Application

Typical uses for this polymer include caster and forklift wheels, screens, cyclones and many other end use applications.

#### Product Specification

<b>% NCO</b>	6.3 ± 0.2
<b>Specific Gravity @ 25°C</b>	1.02
<b>Viscosity @ 80°C (cps)</b>	300 - 800
<b>Colour</b>	Amber

#### Mixing and Curing Conditions

		<b>EMP95A / MOCA</b>	<b>EMP95A / Ethacure 300</b>
<b>Erapol EMP95A</b>	(pph)	100	100
<b>MOCA Level</b>	(pph)	19.0	-
<b>Ethacure 300 Level</b>	(pph)	-	15.3
<b>Recommended % Theory</b>		95	95
<b>Erapol Temperature</b>	(°C)	75 - 85	65 - 75
<b>Curative Temperature</b>	(°C)	110 - 120	20 - 30
<b>Pot Life</b>	(mins)	3	3
<b>Demould Time @ 100°C</b>	(hrs)	1	1
<b>Post Cure Time @ 100°C</b>	(hrs)	16	16

All results are based on 100 grams of **Erapol EMP95A** at 95°C.



This information is of general nature and is supplied without recommendation of guarantee. It does not make claim to be free from patent infringement. Properties shown are typical and do not imply specification tolerances. Era Polymers cannot accept liability for loss or damage through use. Whilst these technical details are based on expert knowledge, practical experience and laboratory testing, successful application depends upon the nature and conditions in which the products are supplied. Users must, by comprehensive testing, evaluate this product in their own application.

## Physical Properties

Properties presented below are to be used as a guide and not intended for specification purposes.

		EMP95A / MOCA	TEST METHOD
<b>Hardness</b>	(Shore A)	95 ± 3	AS1683.15
<b>Tensile Strength</b>	MPa (psi)	37.9 (5497)	AS1683.11
<b>100% Modulus</b>	MPa (psi)	9.7 (1407)	AS1683.11
<b>300% Modulus</b>	MPa (psi)	17.9 (2596)	AS1683.11
<b>Angle Tear Strength, Die C</b>	(kN/m)	95	AS1683.12
<b>Elongation</b>	(%)	400	AS1683.11
<b>DIN Resilience</b>	(%)	45	DIN53512
<b>DIN Abrasion Resistance 10N</b>	(mm <sup>3</sup> )	97	AS1683.21
<b>DIN Abrasion Resistance 5N</b>	(mm <sup>3</sup> )	32	AS1683.21
<b>Compression Set / 22 hr @ 70°C</b>	(%)	42	AS1683.13
<b>Cured Specific Gravity</b>	(g/cm <sup>3</sup> )	1.10	AS1683.4

## Processing Procedure

1. **Erapol EMP95A** should be heated to 80 ± 5°C and thoroughly degassed at 1 - 5mm Hg of vacuum until excessive foaming stops.
2. The curative should be added to **EMP95A**, the MOCA must first be melted at 110 - 120°C prior to mixing and Ethacure 300 processed at room temperature. After adding the curative, mix thoroughly, being careful not to introduce air into the mixture.
3. Pour mixed materials into moulds that have been preheated to 80 - 100°C and pre-coated with release agent.

## Adhesion

Adhesion of Erapol based elastomers to various substrates is at best marginal if a primer is not used. Please consult Era Polymers for specific recommendation to improve adhesion.

## Handling Precautions

**Erapol EMP95A** contains small amounts of free TDI. Therefore the product should be used in well-ventilated areas. Avoid breathing in vapours and protect skin and eyes from contact.

In case of skin contact, immediately remove excess, wash with soap and water. For eye contact, immediately flush with water for at least 15 minutes. Call a physician.

If nose, throat or lungs become irritated from breathing in vapours, remove exposed person to fresh air. Call a physician.